

Ideal for small characters



LAYING CONDITIONS

Temperature	Time	Pressure	Peeling	Washing
140* to 160° C	10 to 12 "	Good	tepid / cold	up to 80°C



■ INTRODUCTION

PromaFlex PU is a polyurethane film of slightly satiny aspect made for fine cuts with 80 microns thickness and an adhesive liner. PromaFlex PU is ideal to peel small characters.

■ CUTTING

It can be cut with a 45° standard blade for flex or with any other kind of blades. The blade and the Teflon strip of your plotter should be in good state. Adjust the pressure so that the blade leaves a slight mark on the plastic base. Be careful not to go through the base. Then make some cutting test before starting your production.

Cut in mirror image.



■ LAYING

After peeling, put your logo on your item to be stamped with the sticky face on the textile which enables an easier adjustment of the logo. Then press it with good pressure at 150°C during 12 seconds. Take off the plastic base tepid or cold.



■ SUPERIMPOSING

Simply proceed in 2 steps :
 Transfer the 1st colour respecting the laying conditions above.
 Take off the plastic base tepid or cold.
 Transfer the 2nd colour with the same laying conditions.

■ WASHING & IRONING

Wash and iron backward.
 Use of dryer unadvised.

for Cotton,
 Polyester,
 Lycra & Nylon

■ LAYING on NYLON

*Tests are required before any production on nylon, lycra or coated items. Transfer from 140°C and wash up to 30°C.